

14 November 2011

MAIDEN ORE RESERVE FOR JAMBREIRO IRON ORE PROJECT

Proven and Probable Ore Reserve of 49Mt grading 28.2% Fe for friable component of Project Resource

- Jambreiro Pre-Feasibility Study (PFS) pit design contains an initial Proven and Probable Ore Reserve of 49Mt grading 28.2% Fe for the friable component of the Jambreiro resource.
- Metallurgical testwork indicates that an initial 17.1Mt of high quality hematite concentrate grading 66.6% Fe, 2.8% SiO₂, 0.7% Al₂O₃ and 0.02% P can be produced from the PFS Ore Reserve.
- Ore Reserve is sufficient for 8.5 years of operations at the planned 2Mtpa concentrate production rate.
- Very low life-of-mine strip ratio of 0.94:1 and free dig nature of the friable ore will result in low operating cash costs.
- Measured, Indicated and Inferred Resources of 64.6Mt grading 25.8% Fe remain outside of the initial Ore Reserve pit limits.
- Further RC drilling is planned to upgrade reserves for the first four years of planned mine life into the Proven category, with this drilling also designed to provide samples for a pilot plant testwork program.

Centaurus Metals (ASX Code: **CTM**) is pleased to announce a **maiden Ore Reserve estimate** for its flagship Jambreiro Iron Ore Project following completion of pit designs as part of the Pre-Feasibility Study ("PFS") on the Project.

The Jambreiro JORC Resource comprises 116.5Mt at an average grade of 26.8% Fe including both near surface friable, and underlying compact, mineralised components. In establishing the maiden Ore Reserve, only the Measured and Indicated components of the friable resource estimate (52.1 Mt at 28.0% Fe) were considered.

The Proven and Probable Ore Reserve has been estimated at **49.0Mt at an average grade of 28.2% Fe** from within the friable Measured and Indicated Resource referred to above, representing a 94% conversion rate. The final pit design includes 46.0Mt of waste movement for a total Life of Mine material movement of 95.0Mt at a strip ratio of 0.94:1. The complete mine schedule is provided in Appendix B to this Announcement.

The Ore Reserve estimation follows an extensive resource drilling program at Jambreiro, metallurgical testwork, open pit design and mine scheduling and capital and operating cost estimations. The resulting average operating cash costs are as follows:

	A\$ per DMT Product	A\$ per tonne material moved
Mine Operating Costs	8.69	1.56
Plant Operating Costs	11.17	
Total Operating Cash Costs	19.86	

**AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT
& MEDIA RELEASE**



Extensive bench scale metallurgical test work has confirmed that a high grade hematite product can be produced from the friable Jambreiro ore. The PFS Ore Reserve is forecast to produce hematite concentrate production of 17.1 million tonnes grading 66.6% Fe and 2.8% SiO₂ which will provide an initial mine life of 8.5 years at the planned production rate of 2Mtpa.

The high quality iron product, with its very low level of impurities, will be highly sought after in the domestic steel industry in Brazil, and initial discussions with potential customers have indicated that a long term consistent supply of high quality iron ore would be well received in the domestic market.

Further RC drilling is planned to commence in November 2011 to upgrade reserves for the first four years of planned mine life into the Proven category, with this drilling designed to provide samples for a pilot plant testwork program and to assist with securing debt funding on a timely basis.

Measured, Indicated and Inferred Resources of 64.6 million tonnes at an average grade of 25.8% Fe remain outside the maiden Reserve initial pit design. It is expected that this material can be upgraded to Reserves and higher categories of Resources with additional drilling. This additional drilling is likely to be undertaken only after production commences. A summary of the Ore Reserves and Mineral Resources are set out in Table 1 with a full table of these Resources and Reserves at Appendix A.

Table 1 – Jambreiro Reserve & Resource Classifications – November 2011

Ore Reserve Classification	Mt	Fe%	SiO ₂ %	Al ₂ O ₃ %	P%	LOI %
Proven	12.0	28.5	51.2	4.5	0.03	1.7
Probable	37.0	28.1	51.0	5.2	0.04	2.2
Total	49.0	28.2	51.1	5.0	0.04	2.1
Concentrate Production	17.1	66.6	2.8	0.69	0.02	0.4
Mineral Resource Classification						
Measured	13.5	28.4	51.0	4.4	0.04	1.7
Indicated	58.5	27.5	50.8	4.5	0.04	1.9
Inferred	44.5	25.4	53.0	4.4	0.05	1.6
Total	116.5	26.8	51.6	4.5	0.04	1.7

Resources are inclusive of Reserves

The open pit locations can be seen on the site layout map at Figure 1 whilst several of the cross sections at Jambreiro can be seen in Figures 2 to 5. The location of the cross sections can be seen on the Project map at Figure 6.

-ENDS-

Released By:

Nicholas Read
Read Corporate
Mb: (+61) 419 929 046
Tel: (+61-8) 9388 1474

On behalf of:

Mr Darren Gordon
Managing Director
Centaurus Metals Ltd
Tel: (+61-8) 9420 4000



AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT & MEDIA RELEASE

Competent Person's Compliance Statement

The information in this report that relates to Exploration Results and Mineral Resources is based on information compiled by Roger Fitzhardinge who is a Member of the Australasia Institute of Mining and Metallurgy and Volodymyr Myadzel who is a Member of Australian Institute of Geoscientists. Roger Fitzhardinge is a permanent employee of Centaurus Metals Limited and Volodymyr Myadzel is the Senior Resource Geologist of BNA Consultoria e Sistemas Limited, independent resource consultants engaged by Centaurus Metals.

Roger Fitzhardinge and Volodymyr Myadzel have sufficient experience which is relevant to the style of mineralization and type of deposit under consideration and to the activity which they are undertaking to qualify as a Competent Person as defined in the 2004 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserve'. Roger Fitzhardinge and Volodymyr Myadzel consent to the inclusion in the report of the matters based on their information in the form and context in which it appears.

The information in this report that relates to Ore Reserves is based on information compiled by Beck Nader who is a professional Mining Engineer and a Member of Australian Institute of Geoscientists. Beck Nader is the Managing Director of BNA Consultoria e Sistemas Ltda and is a consultant to Centaurus.


Beck Nader has sufficient experience, which is relevant to the style of mineralization and type of deposit under consideration and to the activity, which he is undertaking to qualify as a Competent Person as defined in the 2004 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserve'. Beck Nader consents to the inclusion in the report of the matters based on their information in the form and context in which it appears.

Caution Regarding Forward Looking Statements

The forward-looking statements made in this announcement are based on assumptions and judgments of management regarding future events and results. Such forward-looking statements, including but not limited to those with respect to reserve targets or the development of a mine at Jambreiro and the Company's capital expenditures and estimated future production involve known and unknown risks, uncertainties, and other factors which may cause the actual results, performance or achievements of the Company to be materially different from any anticipated future results, performance or achievements expressed or implied by such forward-looking statements. Such factors include, among others, the actual market prices of iron ore, the actual results of current exploration, the actual results of future mining, processing and development activities, changes in project parameters as plans continue to be evaluated, as well as those factors disclosed in the Company's filed documents.



Figure 1 – Jambreiro Site Layout Map showing Open Pit Locations



AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT & MEDIA RELEASE

Figure 2 – Cross Section 1 with Pit Design for Initial Ore Reserve





Figure 3 – Cross Section 4 with Pit Design for Initial Ore Reserve



AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT & MEDIA RELEASE

Figure 4 – Cross Section 7 with Pit Design for Initial Ore Reserve






Figure 5 – Cross Section 15 with Pit Design for Initial Ore Reserve



AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT
 & MEDIA RELEASE



Figure 6 – Jambreiro Magnetic Image with Cross Section Locations



**AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT
& MEDIA RELEASE**



Appendix A
Jambreiro Iron Ore Project – November 2011 JORC Ore Reserve Estimate - By Prospect

Prospect	JORC Category	Million Tonnes	Fe %	SiO ₂ %	Al ₂ O ₃ %	P %	LOI %
Tigre	Proven	12.0	28.6	51.2	4.5	0.03	1.7
	Probable	25.7	27.8	51.7	4.9	0.04	1.9
	TOTAL	37.7	28.0	51.6	4.8	0.04	1.9
Cruzeiro	Proven						
	Probable	4.5	31.0	49.1	3.9	0.04	1.8
	TOTAL	4.5	31.0	49.1	3.9	0.04	1.8
Galo	Proven						
	Probable	6.8	27.1	49.5	7.4	0.04	3.3
	TOTAL	6.8	27.1	49.5	7.4	0.04	3.3
Jambreiro Total	Proven	12.0	28.6	51.2	4.5	0.03	1.7
	Probable	37.0	28.0	51.0	5.2	0.04	2.2
	TOTAL	49.0	28.2	51.1	5.0	0.04	2.1
Friable	Proven	12.0	28.6	51.2	4.5	0.03	1.7
	Probable	37.0	28.0	51.0	5.2	0.04	2.2
	TOTAL	49.0	28.2	51.1	5.0	0.04	2.1

Cut-off 20% Fe

**AUSTRALIAN SECURITIES EXCHANGE ANNOUNCEMENT
& MEDIA RELEASE**



Appendix A (Cont...)

Jambreiro Iron Ore Project – October 2011 JORC Resource Estimate - By Prospect

Prospect	JORC Category	Million Tonnes	Fe %	SiO ₂ %	Al ₂ O ₃ %	P %	LOI %
Tigre (Including South East Extn)	Measured	13.5	28.4	51.0	4.4	0.04	1.7
	Indicated	44.3	27.1	51.3	4.1	0.04	1.6
	Measured + Indicated	57.8	27.4	51.2	4.2	0.04	1.7
	Inferred	27.9	25.6	52.1	3.8	0.05	1.1
	TOTAL	85.7	26.8	51.5	4.1	0.05	1.5
Cruzeiro	Measured						
	Indicated	6.3	30.8	48.6	4.0	0.04	1.8
	Measured + Indicated	6.3	30.8	48.6	4.0	0.04	1.8
	Inferred	2.3	29.4	45.2	6.2	0.06	2.8
	TOTAL	8.6	30.5	47.7	4.6	0.04	2.1
Galo	Measured						
	Indicated	7.9	26.6	49.8	7.5	0.04	3.4
	Measured + Indicated	7.9	26.6	49.8	7.5	0.04	3.4
	Inferred	7.6	25.1	52.5	6.3	0.04	2.9
	TOTAL	15.5	25.9	51.1	6.9	0.04	3.2
Coelho	Inferred	6.7	23.8	59.6	4.3	0.03	1.5
	TOTAL	6.7	23.8	59.6	4.3	0.03	1.5
Jambreiro Total	Measured	13.5	28.4	51.0	4.4	0.04	1.7
	Indicated	58.5	27.5	50.8	4.5	0.04	1.9
	Measured + Indicated	72.1	27.6	50.8	4.5	0.04	1.9
	Inferred	44.5	25.4	53.0	4.4	0.05	1.6
	TOTAL	116.5	26.8	51.6	4.5	0.04	1.7
Friable	Measured	12.1	28.6	51.2	4.6	0.03	1.7
	Indicated	39.9	27.9	51.1	5.3	0.04	2.2
	Measured + Indicated	52.1	28.0	51.1	5.1	0.04	2.1
	Inferred	15.0	24.9	55.2	5.3	0.04	2.1
	TOTAL	67.0	27.3	52.0	5.1	0.04	2.1
Compact	Measured	1.4	27.4	48.8	2.8	0.05	1.6
	Indicated	18.6	26.6	50.2	3.0	0.06	1.2
	Measured + Indicated	20.0	26.6	50.1	3.0	0.05	1.3
	Inferred	29.5	25.7	51.9	4.0	0.05	1.3
	TOTAL	49.5	26.1	51.1	3.6	0.05	1.3
TOTAL		116.5	26.8	51.6	4.5	0.04	1.7

*Cut-off 20% Fe
Resources include Reserves*



Appendix B - Jambreiro Mine Production Schedule

Year	ROM tx10 ³	Fe %	Wet Mass Recovery %	Product tx10 ³	Friable Ore considered waste tx10 ³	Compact Ore tx10 ³	Friable Waste tx10 ³	Compact Waste tx10 ³	Waste tx10 ³	Strip Ratio
	Wet			Dry	Wet	Wet	Wet	Wet	Wet	
1	5,540	29.06	35.94	1,991	168		2,553		2,721	0.49
2	5,600	28.76	35.57	1,992	296	3	2,583	4	2,887	0.52
3	5,596	28.94	35.79	2,003	67		2,929		2,995	0.54
4	5,698	28.14	34.80	1,983	471	0	3,926	0	4,398	0.77
5	5,956	27.85	34.44	2,051	446		4,129		4,575	0.77
6	5,905	27.45	33.95	2,005	613	29	7,833	8	8,484	1.44
7	5,839	27.89	34.50	2,014	542	520	7,247	60	8,370	1.43
8	5,840	27.65	34.20	1,997	2,000	575	5,013	73	7,661	1.31
9(*)	2,994	27.65	34.20	1,024	1,025	295	2,570	37	3,928	1.31
Total	48,966	28.17	34.84	17,060	5,629	1,422	38,782	183	46,017	0.94

(*) – 6 months of operation